

Coloured Oil

 Colouring and protection in one coat

Directions for use

1. Sand as required to 100-120 grit. Previous treatments to old floors should be removed entirely (varnish, oil, waxes).
2. Vacuum the floor. If the floor still has residues of dust, clean the surface with Reeve Cleaner Soap.
3. Add hardener to the oil to speed up curing and improve durability. Stir well. Only mix the amount you intend to use within a 4 hour period as shelf life will be reduced after adding the hardener.
4. Allow 3-4 minutes for the product to react, spread equally across the floor, rub away excess oil within 20 minutes before the floor is touch dry. This can be done manually with a cotton cloth or using a polishing machine with a white or beige pad. As a final wipe use a clean lint free cloth. Try to work in the direction of the wood i.e. along the length of the planks. If you walk on the treated areas, ensure to remove any foot marks when rubbing off the excess. It is advisable to work in areas of three to four plank widths – apply the oil, remove the surface excess and move on to the next area.
5. The floor can be walked on after 24 - 36 hours. During the first 3 weeks the floor should be maintained with a floor wiper that has a dry cloth. After 3 weeks the floor can be maintained with water and Reeve Cleaner Soap.

Warnings

KEEP OUT OF THE REACH OF CHILDREN

WARNING

Cloths saturated with Reeve Coloured Oil can combust. After using, soak cloths in water before disposal. Do not dilute under any circumstances. This product is intended for professional use. It is the responsibility of the user to determine by own testing whether the product is suitable for the chosen application.

HAZARDS

H317 May cause an allergic skin reaction.

H332 Harmful if inhaled.

H335 May cause respiratory irritation.

P280 Wear protective gloves.

P302+P352 If on skin wash with plenty of soap and water.

Hardener

Directions for use

This product is for professional use only. To be used as a hardener in combination with Reeve Coloured Oil. Use 166ml Hardener to 1 litre of Reeve Coloured Oil.

Add the hardener to the oil and stir thoroughly. Only mix the amount you will use within a 4 hour working period, after addition of the hardener the shelf life will be reduced.

Warnings

KEEP OUT OF THE REACH OF CHILDREN

HAZARDS

H317 May cause an allergic skin reaction.

H332 Harmful if inhaled.

H335 May cause respiratory irritation.

P280 Wear protective gloves.

P302+P352 If on skin wash with plenty of soap and water.